

PRODUCT CODE	TİSLAMİD A 10 D03 K04 R01
PRODUCT DESCRIPTION	PA6, 10% GLASS FIBER REINFORCED, IMPACT MODIFIED, NATURAL

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.18-1.21
	MOLDING SHRINKAGE	PARALLEL	ISO 294-4	%	0.2-0.45
	MOISTURE CONTENT	-	ISO 15512	%	<0.2

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	100-110
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	-
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	<3
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	4500-5500
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	7-10
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	kJ/m ²	-

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	-
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	225
	BALL PRESSURE TEST	-	ISO 60695-10-2	-	-

PRODUCT CODE	TİSLAMİD A 10 D03 K04 R01
PRODUCT DESCRIPTION	PA6, 10% GLASS FIBER REINFORCED, IMPACT MODIFIED, NATURAL

ELECTRICAL&FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	HB
	FLAME RATING	1,6 mm	UL 94	-	HB
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	-
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	500
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+14
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	1E+15

INJECTION PROCESS	ÖZELLİKLERİ	BİRİM	DEĞER
	PREDRYING TEMPERATURE	°C	100--120
	PREDRYING TIME	Hours	3-4
	MELTING TEMPERATURE	°C	230-250
	NOZZLE TEMPERATURE	°C	210-230
	PRE- 3 REGION TEMPERATURE	°C	240-260
	MID-2 REGION TEMPERATURE	°C	240-260
	AFT-1 REGION TEMPERATURE	°C	240-260
	MOLD TEMPERATURE	°C	50-90
	HOLD PRESSURE	MPa	50-100