

PRODUCT CODE	TİSLAMİD B UNR F02 Y01 R01
PRODUCT DESCRIPTION	PA66, FLAME RETARDANT-HALOGEN FREE, NATURAL

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.17-1.20
	MOLDING SHRINKAGE	PARALLEL/NORMAL	ISO 294-4	%	0.4/1.3
	MOISTURE CONTENT	-	ISO 15512	%	<0.2

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	70-80
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	-
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	-
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	3500-4000
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	4-5
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	kJ/m ²	3-4
	IZOD IMPACT STRENGTH, UNNOTCHED	+23°C	ISO 180/U	kJ/m ²	-
	IZOD IMPACT STRENGTH, UNNOTCHED	-30°C	ISO 180/U	kJ/m ²	-

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	245
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	225
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	85
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	260-265
	BALL PRESSURE TEST	120 °C	ISO 60695-10-2	-	-

PRODUCT CODE	TİSLAMİD B UNR F02 Y01 R01
PRODUCT DESCRIPTION	PA66, FLAME RETARDANT-HALOGEN FREE, NATURAL

ELECTRICAL & FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	V0
	FLAME RATING	1,6 mm	UL 94	-	V0
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	960
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	775
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	600
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+15
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	1E+13

INJECTION PROCESS	PROPERTIES	UNITS	VALUE
	PREDRYING TEMPERATURE	°C	90-110
	PREDRYING TIME	Hours	3-4
	MELTING TEMPERATURE	°C	260-290
	NOZZLE TEMPERATURE	°C	250-270
	PRE- 3 REGION TEMPERATURE	°C	270-290
	MID-2 REGION TEMPERATURE	°C	270-290
	AFT-1 REGION TEMPERATURE	°C	270-290
	MOLD TEMPERATURE	°C	80-100
	HOLD PRESSURE	MPa	50-100