

PRODUCT CODE	TISOPLÉN C F01 Y03 K01 HS R10
PRODUCT DESCRIPTION	PPH, FLAME RETARDANT-HALOGEN (RoHS COMPLIANCE), ANTI-STATIC, WHITE

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.03-1.06
	MOLDING SHRINKAGE	PARALLEL/NORMAL	ISO 294-4	%	-
	MOISTURE CONTENT	-	ISO 15512	%	-

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	-
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	20-25
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	>50
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	900-1200
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	35-40
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	kJ/m ²	-
	IZOD IMPACT STRENGTH, UNNOTCHED	+23°C	ISO 180/U	kJ/m ²	-
	IZOD IMPACT STRENGTH, UNNOTCHED	-30°C	ISO 180/U	kJ/m ²	-

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	40
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	165-170
	BALL PRESSURE TEST	120 °C	ISO 60695-10-2	-	-

PRODUCT CODE	TISOPLÉN C F01 Y03 K01 HS R10
PRODUCT DESCRIPTION	PPH, FLAME RETARDANT-HALOGEN (RoHS COMPLIANCE), ANTI-STATIC, WHITE

ELECTRICAL & FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	V2
	FLAME RATING	1,6 mm	UL 94	-	V2
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	860
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	775
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+10
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	1E+10

INJECTION PROCESS	PROPERTIES	CONDITION	VALUE
	PREDRYING TEMPERATURE	°C	80
	PREDRYING TIME	hours	1-2
	MELTING TEMPERATURE	°C	210-230
	NOZZLE TEMPERATURE	°C	230
	PRE- 3 REGION TEMPERATURE	°C	200-240
	MID-2 REGION TEMPERATURE	°C	200-240
	AFT-1 REGION TEMPERATURE	°C	150-180
	MOLD TEMPERATURE	°C	40-70
	HOLD PRESSURE	MPa	50-100