

UBESTA 3030J15

Technical Product Information

UBESTA 3030J15 is a plasticized and impact modified Polyamide 12 suitable for pneumatic and air brake tubes. Material complies with DIN 73378 – PA12 HIPHL, Type I and SAE J844. This material has following features:

- Excellent mechanical properties
- High impact strength
- Excellent processability

Basic Properties ⁽¹⁾		Method	Unit	Value
Polymer		-	-	PA12
Colour		-	-	Natural
Density		ISO 1183-3	g/cm ³	1,01
Melting Point		ISO 11357	°C	173
MFI @ 235 °C, 2,16 Kg		ISO 1133	g/10 min	4
Shore Hardness	D scale	ISO 868	-	67
Rockwell Hardness	R scale	ISO 2039-2	-	51

Mechanical Properties ⁽²⁾		Method	Unit	Value
Tensile stress at yield		ISO 527-1,2	MPa	26
Tensile strain at yield			%	24
Tensile strain at break			%	> 150
Flexural strength		ISO 178	MPa	19
Flexural modulus			MPa	400
Charpy impact strength (notched) ⁽³⁾	23 °C	ISO 179/1eA	kJ/m²	115 P
	-40 °C		kJ/m²	4 C


Thermal Properties ⁽²⁾		Method	Unit	Value
Temp. of deflection under load	0,45 MPa	ISO 75-2	°C	91
	1,80 MPa		°C	45
Coefficient of linear expansion		ISO 11359-2	x 10 ⁻⁴ /K	1,7

Note: All tests carried dry as mould

(1) Measured on pellets

(2) Measured on injection-moulded specimens, based on ISO type

(3) P=partial break, C=complete break



Processing conditions

	Extruder						Die
	Hopper	Zone 1	Zone 2	Zone 3	Zone 4	Adaptor	
Temperature (°C)	40 - 120	190 - 210	200 - 220	220 - 240	220 - 240	220 - 240	220 - 240

Drying conditions

UBESTA is supplied dry (moisture content < 0,1%) and packed in high barrier films. However, as polyamide is a hygroscopic material, the user should take a special care of the possible moisture absorption once the bag or liner box has been opened. In case of moisture absorption, the material should be dried with dehumidified air at 80°C for more than 4 hours.

Storage

Well-sealed packages could be stored in cool and dry conditions over long periods of time. Protect the packages from heat and direct sunlight to prevent possible damages.

