

VYLOPET™ EMC-730L
TOYOBO MC Corporation - Polybutylene Terephthalate

General Information			
Product Description			
GF Reinforced			
General			
Material Status	• Commercial: Active		
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Hydrolysis Resistant		
Uses	• Automotive Applications • General Purpose • Electrical/Electronic Applications • Industrial Applications		
Forms	• Pellets		
Processing Method	• Injection Molding		
Part Marking Code (ISO 11469)	• >PBT-GF30<		
Revision Date	• 9/10/2025		
ASTM & ISO Properties			
Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm³	ISO 1183
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	0.20	%	
Across Flow : 2.00 mm	1.1	%	
Water Absorption (24 hr, 23°C)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	131	MPa	ISO 527
Tensile Strain (Break)	2.3	%	ISO 527
Flexural Modulus	8600	MPa	ISO 178
Flexural Strength	200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.5	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	2.0E-5	cm/cm/°C	
Transverse	9.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+13	ohms·m	IEC 62631-3-1



VYLOPET™ EMC-730L

TOYOBO MC Corporation - Polybutylene Terephthalate

Processing Information		
Injection		Unit
Middle Temperature	260 to 275	°C
Front Temperature	260 to 275	°C
Nozzle Temperature	260 to 275	°C
Mold Temperature	50 to 90	°C

Notes

¹ 100×100×2mmt, film gate

