

**DURACON® TW-51**

Polyplastics - Acetal (POM) Copolymer + PE

## General Information

Product Description	
High Sliding	
High Rigidity, Low Warpage	
General	
Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• Copolymer • Low Friction • High Rigidity • Low Warpage
UL File Number	• E45034
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >POM+PE-MD30<

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.2	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	1.6	%	
Flow : 0.0787 in	1.7	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	703000	psi	ISO 527-1
Tensile Stress	5800	psi	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Modulus	645000	psi	ISO 178
Flexural Stress	10400	psi	ISO 178
Coefficient of Friction			JIS K7218
Dynamic <sup>3</sup>	0.22		
vs. Steel - Dynamic <sup>4</sup>	0.30		
Wear Factor			JIS K7218
140 psi, 59 ft/min <sup>5</sup>	< 0.50	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	
140 psi, 59 ft/min <sup>6</sup>	50	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	
8.7 psi, 30 ft/min <sup>7</sup>	150	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	
8.7 psi, 30 ft/min <sup>8</sup>	150	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	0.95	ft·lb/in <sup>2</sup>	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	50		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	194	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	5.0E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	5.0E-5	in/in/°F	Internal Method
Flammability	Nominal Value	Unit	Test Method



Flame Rating	HB	UL 94
<b>Additional Information</b>	<b>Nominal Value</b>	<b>Unit</b>
Color Number	CF2001	

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60×60×2mmt, Cavity Pressure 60 MPa

<sup>3</sup> vs M90-44, 0.06 MPa, 15 cm/s

<sup>4</sup> 0.98 MPa, 30 cm/s

<sup>5</sup> vs C-Steel, Steel Side

<sup>6</sup> vs C-Steel, Material Side

<sup>7</sup> vs M90-44, Material Side

<sup>8</sup> vs M90-44, M90-44 Side

