

HiFill® PP GF10 CC

 Techmer Polymer Modifiers - *Polypropylene*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight
Features	• Chemically Coupled
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	0.980		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.010	%	ASTM D570
Mechanical			
Tensile Strength (Break)	8000	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	400000	psi	ASTM D790
Flexural Strength	10000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.5	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	7.5	ft·lb/in	ASTM D4812
Hardness			
Rockwell Hardness (R-Scale)	85		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	275	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	270	°F	ASTM D648
Melting Temperature	325	°F	
CLTE - Flow	3.0E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	550	V/mil	ASTM D149
Flammability			
Flame Rating	HB		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
