

InStruc® PA66PA6IGF60HS

Americhem - Polyamide 66 + PA 6I/6T

General Information
Product Description

60% GLASS FIBER REINFORCED, HEAT STABILIZED NYLON 6/6 + NYLON 6I/6T

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 60% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Filled • Good Dimensional Stability	• Heat Stabilized • High Stiffness	• High Strength
Uses	• Closures • Consumer Applications • Electrical/Electronic Applications • Engineering Parts	• Household Goods • Industrial Applications • Industrial Parts • Office Automation Equipment	• Outdoor Applications • Window & Door Components
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.70		ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.95E+6	psi	ASTM D638
Tensile Strength	33000	psi	ASTM D638
Tensile Elongation (Yield)	2.0	%	ASTM D638
Flexural Modulus	3.00E+6	psi	ASTM D790
Flexural Strength	56000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	2.7	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	480	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	ASTM D257

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Drying Time	4.0	hr
Processing (Melt) Temp	520 to 570	°F
Mold Temperature	180 to 250	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

Notes
¹ Typical properties: these are not to be construed as specifications.
