

**LATER 4-V0**

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polybutylene Terephthalate*
**General Information**
**Product Description**

Compound based on Polybutylene Terephthalate (PBT). Flame retardant, UL94 V-0 class, with brominated flame retardants, free of PBB/PBDE and antimony trioxide.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Brominated	• Flame Retardant	

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.42	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	1.5 to 1.8	%	
Flow : 0.0787 in	1.5 to 1.8	%	
Water Absorption <sup>3</sup> (Saturation, 73°F)	0.18	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	406000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	7250	psi	ISO 527-2/5
Tensile Stress (Break, 73°F)	5800	psi	ISO 527-2/5
Tensile Strain (Yield, 73°F)	3.0	%	ISO 527-2/5
Tensile Strain (Break, 73°F)	20	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	40	ft·lb/in <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	311	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	131	°F	ISO 75-2/A
Vicat Softening Temperature	338	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	6.7E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	6.7E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
-- <sup>4</sup>	1.4	Btu·in/hr/ft <sup>2</sup> /°F	
-- <sup>5</sup>	1.4	Btu·in/hr/ft <sup>2</sup> /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	530	V/mil	ASTM D149
Comparative Tracking Index <sup>6</sup> (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.030 in	V-0		
0.06 in	V-0		
0.12 in	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
0.04 in	1760	°F	
0.08 in	1760	°F	



Glow Wire Ignition Temperature		IEC 60695-2-13
0.04 in	1290 °F	
0.08 in	1290 °F	
Oxygen Index	30 %	ASTM D2863

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60 MPa

<sup>3</sup> in air

<sup>4</sup> through plane

<sup>5</sup> in plane

<sup>6</sup> Without surfactant

