

LONGLITE® PMC T373J60

Chang Chun Plastics Co., Ltd. (CCP Group) - Phenolic

General Information
Product Description

PMC T 373 J60 is a granular wood flour reinforced phenolic product for injection moulding

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Wood Flour		
Features	• Chemical Resistant • Fuel Resistant • Good Electrical Properties	• Good Moldability • Good Weather Resistance • High Heat Resistance	• Oil Resistant • Solvent Resistant • Wear Resistant
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.42		ASTM D792
Density	1.42	g/cm ³	ISO 1183
Molding Shrinkage	0.90 to 1.3	%	ISO 2577
Water Absorption (24 hr)	0.30	%	ASTM D570
Water Absorption (24 hr, 73°F)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	7980	psi	ASTM D638
Tensile Stress (Yield)	7980	psi	ISO 527-2
Flexural Strength	10700	psi	ASTM D790
Flexural Stress	10700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.250 in)	0.55	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	338	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	338	°F	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10	ohms	ASTM D257
Surface Resistivity	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+12	ohms·cm	ASTM D257
Volume Resistivity	1.0E+12	ohms·cm	IEC 60093
Dielectric Strength (0.0787 in)	300	V/mil	ASTM D149
Electric Strength (0.0787 in)	300	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.08 in)	V-0		UL 94

Additional Information

Spiral Flow, CCP: 51 to 70 cm

 Density, ASTM D792 & ISO 1183: 1.41 to 1.43 g/cm³

Maximum application temperature, IEC 60216-P1, 50 hr: 200°C

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	104 to 194	°F
Middle Temperature	104 to 194	°F
Front Temperature	104 to 194	°F
Nozzle Temperature	185 to 221	°F



Processing (Melt) Temp	230 to 248 °F
Mold Temperature	329 to 383 °F
Injection Rate	Moderate-Fast
Back Pressure	< 145 psi
Screw Speed	30 to 50 rpm

Injection Notes

Injection Time: 5 ± 2 sec
Hardening Time: 15 ± 5 sec

Notes

¹ Typical properties: these are not to be construed as specifications.

