

LONGLITE® PMC T375JX

Chang Chun Plastics Co., Ltd. (CCP Group) - Phenolic

General Information
Product Description

PMC T 375 JX is a wood flour and mineral reinforced phenolic injection moulding compound with improved heat resistance

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Mineral	• Wood Flour	
Features	• Chemical Resistant	• Good Moldability	• Oil Resistant
	• Fuel Resistant	• Good Weather Resistance	• Solvent Resistant
	• Good Electrical Properties	• High Heat Resistance	• Wear Resistant
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.51		ASTM D792
Density	1.51	g/cm ³	ISO 1183
Molding Shrinkage	0.50 to 1.0	%	ISO 2577
Water Absorption (24 hr)	0.16	%	ASTM D570
Water Absorption (24 hr, 73°F)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength	13100	psi	ASTM D790
Flexural Stress	13100	psi	ISO 178
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	358	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	358	°F	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.1E+9	ohms·cm	ASTM D257
Volume Resistivity	2.1E+9	ohms·cm	IEC 60093
Dielectric Strength (0.0787 in)	330	V/mil	ASTM D149
Electric Strength (0.0787 in)	330	V/mil	IEC 60243-1
Arc Resistance	150	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.04 in)	V-0		UL 94

Additional Information

Spiral Flow, CCP: 68 cm
 Heat Resistance, IEC 60216-P1, 2 hr: 200°C
 Charpy Impact, JIS K7111: 3.45 kg cm/cm²

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	104 to 194	°F
Middle Temperature	104 to 194	°F
Front Temperature	104 to 194	°F
Nozzle Temperature	185 to 221	°F
Processing (Melt) Temp	230 to 248	°F
Mold Temperature	329 to 383	°F
Injection Rate	Moderate-Fast	
Back Pressure	< 145	psi
Screw Speed	30 to 50	rpm



Injection Notes

Injection Time: 5 ± 2 sec
Hardening Time: 15 ± 5 sec

Notes

¹ Typical properties: these are not to be construed as specifications.

