

LUVOCOM® AC-80/TF/22/BK

LEHOSS Group - Acetal (POM) Copolymer

General Information

Product Description

with PTFE; black

Main Features

- Low warpage.
- Improved friction and wear behaviour. Optimised for dry running operations.
- Sliding-couples with a low friction coefficient.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• PTFE Lubricant		
Features	• Low Friction	• Lubricated	
	• Low Warpage	• Wear Resistant	
Appearance	• Black		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F)	0.18	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	334000	psi	ISO 527-1/1
Tensile Stress	6380	psi	ISO 527-2
Tensile Strain (Yield)	7.0	%	ISO 527-2/50
Flexural Modulus ²	305000	psi	ISO 178
Flexural Stress ³	9430	psi	ISO 178
Flexural Strain - (Yield) ⁴	9.0	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	3.3	ft·lb/in ²	
-22°F	2.4	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
--	24	ft·lb/in ²	
-22°F	19	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	185	°F	ISO 75-2/A
Continuous Use Temperature ⁵	212	°F	IEC 60216
Vicat Softening Temperature	293	°F	ISO 306/A
Service Temperature - during lifetime max. 200 hr	248	°F	
Electrical	Nominal Value	Unit	Test Method
Insulation Resistance ⁶	> 1.0E+12	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		Internal Method

Processing Information

Injection	Nominal Value	Unit
Drying Temperature Circulation Dryer, B	248	°F



Desiccant Dryer, A	167 °F
Drying Time	
Circulation Dryer, B	2.0 to 4.0 hr
Desiccant Dryer, A	2.0 to 8.0 hr
Rear Temperature	347 to 374 °F
Middle Temperature	365 to 401 °F
Front Temperature	356 to 392 °F
Nozzle Temperature	347 to 392 °F
Mold Temperature	176 to 248 °F

Injection Notes

Avoid melt temperature above 215°C! Ventilation of machinery is recommended.

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 0.39 in/min

⁴ 10 mm/min

⁵ 20,000 hr

⁶ strip electrode R25

