

**TAFMER™ A-20090**

Mitsui Chemicals America, Inc. - *Polyalphaolefin*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Forms	• Pellets

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	0.890	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	18	g/10 min	ASTM D1238
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-94.0	°F	ASTM D746
Vicat Softening Temperature	140	°F	ASTM D1525
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms·cm	ASTM D257
Dielectric Strength	1400	V/mil	ASTM D149
Dielectric Constant	2.10		ASTM D150
Dissipation Factor	1.3E-4		ASTM D150

**Additional Information**

Tensile Strength @ Break, JIS K 6301: 160 kgf/cm<sup>2</sup>  
Elongation @ Break, JIS K 6301: 750%  
Surface Hardness, JIS K 6301, A Scale: 86

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
