

TAFMER™ A-4070S

Mitsui Chemicals America, Inc. - *Polyalphaolefin*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Features	• Good Flexibility
Forms	• Pellets

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.870	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	3.6	g/10 min	
230°C/2.16 kg	6.7	g/10 min	
Mooney Viscosity (ML 1+4)	16	MU	JIS K6395
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	> 1160	psi	ASTM D638
Tensile Elongation (Break)	> 1000	%	ASTM D638
Torsional Rigidity	435	psi	ASTM D1043
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -94.0	°F	ASTM D746
Vicat Softening Temperature	106	°F	ASTM D1525
Melting Temperature	131	°F	ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Dielectric Constant	2.20 to 2.40		ASTM D150
Dissipation Factor	< 5.0E-4		ASTM D150

