

**TES J-71/30/V0/ND BK2791**

 Techmer Polymer Modifiers - *Polyamide + SAN*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>		
Availability	<ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>Europe</li> <li>Latin America</li> </ul>	<ul style="list-style-type: none"> <li>North America</li> </ul>
RoHS Compliance	<ul style="list-style-type: none"> <li>RoHS Compliant</li> </ul>		
Forms	<ul style="list-style-type: none"> <li>Pellets</li> </ul>		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.56		ASTM D792
Water Absorption (24 hr)	0.75	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	18100	psi	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Flexural Modulus	1.38E+6	psi	ASTM D790
Flexural Strength	26100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	3.5	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.13 in)	V-0		UL 94

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
