

TRIEX® Compound DMF3000S

Samyang Corporation - Polycarbonate

General Information

Product Description

Polycarbonates provides excellent mechanical properties, dimensional stability, and good electrical property. Widely used in various industrial fields such as electronics, automobiles.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Features	• Flame Retardant
Uses	• General Purpose
Forms	• Pellets

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.40		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7820	psi	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	356000	psi	ASTM D790
Flexural Strength (Yield)	12100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	3.7	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	248	°F	ASTM D648
CLTE - Flow	3.3E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	ASTM D257
Dielectric Strength	760	V/mil	ASTM D149
Dielectric Constant	2.90		ASTM D150
Dissipation Factor	9.0E-3		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

