

Thermylene® P-9900-0712

Asahi Kasei Plastics North America Inc. - *Polypropylene*

General Information

Product Description

This compound has been optimized for improved impact resistance and is heat stabilized for high temperature exposed applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Heat Stabilizer		
Features	• Good Impact Resistance	• Heat Stabilized	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	17	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	4790	psi	ISO 527-2
Flexural Modulus	261000	psi	ISO 178
Flexural Stress	6670	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.4	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	140	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.

