

Thermylene® P6-30FG-0600R

Asahi Kasei Plastics North America Inc. - *Polypropylene*

General Information

Product Description

This general purpose polypropylene compound made with PIR stream and has been heat stabilized for underhood applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Recycled Content	• Post-Industrial (PIR)/Pre-Consumer		
Features	• General Purpose	• Heat Stabilized	
Uses	• Automotive Under the Hood		
Automotive Specifications	• FORD WSS-M4D732-A5	• GM GMP.PP.017 Color: BK711 Black	• STELLANTIS MS-DB-500 CPN 3580

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	11500	psi	ISO 527-2
Flexural Modulus	827000	psi	ISO 178
Flexural Stress	17000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.3	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	286	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.

