

Thermylene® P6-30FG-0708

Asahi Kasei Plastics North America Inc. - *Polypropylene*

General Information

Product Description

This polypropylene compound has been designed for enhanced impact resistance. It may be suitable for some extrusion applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Good Impact Resistance		
Automotive Specifications	• GM GMP.PP.003 Color: BK711		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.4	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	9280	psi	ISO 527-2
Flexural Modulus	783000	psi	ISO 178
Flexural Stress	14800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	9.0	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	282	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.

