

Toyolac™ 100G-30Toray Industries, Inc. - *Acrylonitrile Butadiene Styrene***General Information****Product Description**

GF30%

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• High Strength
Uses	• Automotive Applications • Bathroom Accessories • Automotive Interior Parts • General Purpose
Processing Method	• Injection Molding
ISO Designation	• >ABS-GF30<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.26	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (240°C/10.0 kg)	13	g/10 min	ISO 1133
Molding Shrinkage ²	0.10 to 0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (73°F)	15800	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.0	%	ISO 527-2
Flexural Modulus (73°F)	1.30E+6	psi	ISO 178
Flexural Stress (73°F)	25400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.3	ft·lb/in ²	ISO 179
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	125		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	221	°F	ISO 75-2/A
Vicat Softening Temperature	203	°F	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes¹ Typical properties: these are not to be construed as specifications.² 23°C/50%RH