

Toyolac™ 532 X02

Toray Industries, Inc. - Acrylonitrile Butadiene Styrene

General Information

Product Description

High sliding

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Low Friction		
Uses	• Appliances • Camera Applications • Office Automation Equipment	• Printer • Structural Parts • Video Equipment	• White Goods & Small Appliances
Processing Method	• Injection Molding		
ISO Designation	• >ABS<		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	22	g/10 min	ISO 1133
Molding Shrinkage ²	0.40 to 0.60	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (73°F)	7980	psi	ISO 527-2
Tensile Strain (Break, 73°F)	6.0	%	ISO 527-2
Flexural Modulus (73°F)	390000	psi	ISO 178
Flexural Stress (73°F)	11500	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	5.7	ft-lb/in ²	ISO 179
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	115		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	181	°F	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

² 23°C/50%RH

