

Vydyne® R530H BK08

Ascend Performance Materials Operations LLC - *Polyamide 66*

General Information

Product Description

Vydyne R530H BK08 is a general purpose, 30% glass-filled, heat-stabilized PA66 based resin designed for injection molding applications. R530H BK08 offers improved flow with an improved black surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer	• Lubricant	
Features	• Antifreeze Resistant • Chemical Resistant • Fatigue Resistant	• Gasoline Resistant • Heat Stabilized • High Flow	• Lubricated • Outstanding Surface Finish • Solvent Resistant
Agency Ratings	• ASTM D4066 PA012G30	• ASTM D6779 PA012G30	
Automotive Specifications	• AISIN TO20141124 - P-PA66-GF30-807 • CHERRY Q/SQR.S1-33-2012 CMP.PA66.G6	• FORD WSS-M4D752-B1 • GM GMW16270P-PA66-GF30	• GM GMW3038P-PA66-GF30H • GM GMW3038P-PA66-GF30J
UL File Number	• E70062		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID	• PA66-GF30		

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.90	--	%	
Flow : 73°F, 0.0787 in	0.40	--	%	
Water Absorption (24 hr, 73°F)	0.90	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.45E+6	1.07E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	28300	19600	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	5.0	%	ISO 527-2
Flexural Modulus (73°F)	1.39E+6	870000	psi	ISO 178
Flexural Stress (73°F)	39200	27600	psi	ISO 178
Poisson's Ratio (73°F)	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	4.8	5.2	ft·lb/in ²	
73°F	5.2	6.2	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	31	38	ft·lb/in ²	
73°F	36	40	ft·lb/in ²	
Notched Izod Impact Strength				ISO 180/1A
-22°F	4.8	5.2	ft·lb/in ²	
73°F	5.7	6.2	ft·lb/in ²	



Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	500	--	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	482	--	°F	ISO 75-2/A
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	1.2E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.9E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746B
0.030 in	284	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
RTI Imp				UL 746B
0.030 in	248	--	°F	
0.06 in	248	--	°F	
0.12 in	248	--	°F	
RTI Str				UL 746B
0.030 in	257	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0394 in)	1.0E+13	--	ohms·cm	IEC 60093
Electric Strength (0.0394 in)	510	--	V/mil	IEC 60243-1
Arc Resistance (0.118 in)	PLC 6	--		ASTM D495
Comparative Tracking Index (0.118 in)	250 to 399	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR) (0.118 in)	PLC 1	--		UL 746A
Hot-wire Ignition (HWI)				UL 746A
0.030 in	PLC 4	--		
0.06 in	PLC 3	--		
0.12 in	PLC 4	--		
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.0787 in)	0.0	--	in/min	ISO 3795
Flame Rating				UL 94
0.030 in	HB	--		
0.06 in	HB	--		
0.12 in	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 in	1250	--	°F	
0.06 in	1250	--	°F	
0.12 in	1250	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 in	1290	--	°F	
0.06 in	1290	--	°F	
0.12 in	1290	--	°F	

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Rear Temperature	536 to 590	°F
Middle Temperature	536 to 590	°F
Front Temperature	536 to 590	°F
Nozzle Temperature	536 to 590	°F
Processing (Melt) Temp	545 to 581	°F
Mold Temperature	149 to 203	°F

