

ACRYREX® CM-207G

CHI MEI CORPORATION - *Polymethyl Methacrylate Acrylic*

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
RoHS Compliance	• RoHS Compliant		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.19	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/3.8 kg)	11	cm ³ /10min	ISO 1133
Water Absorption (24 hr, 73°F)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	996	psi	ISO 527-2/5
Tensile Strain (Break)	7.0	%	ISO 527-2/5
Flexural Stress ²	1380	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	0.95	ft·lb/in ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	198	°F	ISO 75-2/A
Deflection Temperature Under Load (264 psi, Annealed)	208	°F	ISO 75-2/A
Vicat Softening Temperature	228	°F	ISO 306/A50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ISO 489
Light Transmittance (118.1 mil)	> 92.0	%	ISO 13468

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

