

EVATANE® 33-45

EVATANE® 33-45 is a random ethylene-vinyl acetate copolymer.

- The high Vinyl Acetate content of EVATANE® 33-45 brings softness, flexibility and polarity. EVATANE® 33-45 is compatible with most tackifying resins and waxes. It is an efficient and easy handling product for hot melt adhesives formulations.
- EVATANE® 33-45 delivers high cohesive strength with most fillers and can be used to produce HFFR compounds. It can also be used as an additive for crude oil (pour point depressant), or bitumen modification. It is an ideal base polymer for semi-conductive compounds for medium voltage cables.

Typical Properties

	Test Method	Unit	Typical Value
Vinyl Acetate Content	FTIR (internal method)	%.-wt.	33
Melt Index (190°C/2.16kg)	ISO 1133	g/10min.	45
Melting Point	ISO 11357-3	°C	62
Density	ISO 1183	g/cm ³	0.96
Vicat Softening Temperature (10N) ¹	ISO 306 / ASTM D1525	°C	<40
Ring & Ball Temperature	ASTM E28 / NF EN 1238	°C	107
Elongation at Break ¹	ISO 527-2 / ASTM D638	%	1100
Tensile Strength at Break ¹	ISO 527-2 / ASTM D638	MPa	9
Hardness Shore A ¹	ISO 868 / ASTM D2240		63

¹: On compression molded samples.



Processing

EVATANE® 33-45 can be processed on most conventional equipment used for thermoplastics. It is recommended to avoid melt temperatures above 230°C and to purge the equipment after a run is completed.

Storage, Handling & Safety

EVATANE® 33-45 should be stored away from heat, humidity and UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

