

TECHNICAL DATA SHEET

[English Units]



TOPAS® 5013L-10

Cyclic Olefin Copolymer (COC)

1,53

Property	Value	Unit	Test Standard
Physical Properties			
Density	1020	kg/m ³	ISO 1183
Melt volume rate (MVR) (260°C, 2.16kg)	48	cm ³ /10min	ISO 1133
Melt flow rate (MFR) (260°C, 2.16kg)	43	g/10min	calculated
Water absorption (23°C-sat)	0,01	%	ISO 62
Mechanical Properties			
Tensile modulus (1mm/min)	460	kpsi	ISO 527-3
Tensile stress at break (5mm/min)	6700	psi	ISO 527-3
Tensile strain at break (5mm/min)	1,7	%	ISO 527-3
Charpy impact strength @ 23°C	6,2	ft-lbs/in ²	ISO 179/1eU
Charpy notched impact strength @ 23°C	0,8	ft-lbs/in ²	ISO 179/1eA
Thermal Properties			
Glass transition temperature (20°C/min)	273	°F	ISO 11357-1,-2
DTUL @ 0.45 MPa	261	°F	ISO 75-1, -2
Vicat softening temperature B50 (50°C/h 50N)	271	°F	ISO 306
Flammability @1.6mm nom. thickn.	HB	Class	UL94
Electrical Properties			
Relative permittivity at 1-10 kHz	2,35	-	IEC 60250
Volume resistivity	<1E14	ohm×m	IEC 60093
Comparative tracking index CTI	>600	-	IEC 60112
Optical Properties			
Deg. of light transmission (t=2mm)	91,4	%	ISO 13468-1
Haze (t=2mm)	<0,6	%	ISO 14782
Refractive index (589nm, 25°C)	1,533	-	ISO 489

