



<b>Bakelite® PF 2121</b>			
PF			Momentive Specialty Chemicals
<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Charpy impact strength (+23°C)	3	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	1	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	1E7	Ohm*m	IEC 60093
Surface resistivity	1E8	Ohm	IEC 60093
<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Density	1400	kg/m <sup>3</sup>	ISO 1183
<b>Characteristics</b>			
<b>Processing</b>			
Injection Molding, Compression Molding			