

TECHNICAL DATA SHEET

DURACON® SW-01

Polyplastics
(POM+PE)-X10

Features

Tribologic grade

Processing/Physical Characteristics	Value	Unit	Standard
Melt volume-flow rate, MVR	6	cm ³ /10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Molding shrinkage, parallel	2.4	%	ISO 294-4, 2577
Molding shrinkage, normal	2.2	%	ISO 294-4, 2577
Mechanical Properties	Value	Unit	Standard
Tensile modulus	2700	MPa	ISO 527
Tensile strength	50	MPa	ISO 527
Nominal strain at break	20	%	ISO 527
Poisson's ratio	0.35		ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	75	MPa	ISO 178
Charpy notched impact strength, +23°C	5.4	kJ/m ²	ISO 179/1eA
Rockwell hardness	M 70		ISO 2039-2
Thermal Properties	Value	Unit	Standard
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow card available	yes		

DURACON® SW-01

Polyplastics

Electrical Properties	Value	Unit	Standard
Volume resistivity	2E12	Ohm*m	IEC 62631-3-1
Electric strength	18	kV/mm	IEC 60243-1
Other Properties	Value	Unit	Standard
Density	1420	kg/m ³	ISO 1183

Diagrams

