

TECHNICAL DATA SHEET

# DURACON® SW-01LV

Polyplastics  
(POM+PE)-X10

**Features**

Tribologic grade

Processing/Physical Characteristics	Value	Unit	Standard
Melt volume-flow rate, MVR	6	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Molding shrinkage, parallel	2.4	%	ISO 294-4, 2577
Molding shrinkage, normal	2.2	%	ISO 294-4, 2577
Mechanical Properties	Value	Unit	Standard
Tensile modulus	2700	MPa	ISO 527
Tensile strength	50	MPa	ISO 527
Nominal strain at break	20	%	ISO 527
Poisson's ratio	0.35		ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	75	MPa	ISO 178
Charpy notched impact strength, +23°C	5.4	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal Properties	Value	Unit	Standard
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow card available	yes		
Other Properties	Value	Unit	Standard
Density	1420	kg/m <sup>3</sup>	ISO 1183