

TECHNICAL DATA SHEET

# DURACON® YF-20

Polyplastics  
(POM+PTFE)

**Additives**

Lubricants

**Features**

Tribologic grade

Processing/Physical Characteristics	Value	Unit	Standard
Melt volume-flow rate, MVR	3.9	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Molding shrinkage, parallel	2.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.7	%	ISO 294-4, 2577
Mechanical Properties	Value	Unit	Standard
Tensile modulus	2100	MPa	ISO 527
Tensile strength	44	MPa	ISO 527
Nominal strain at break	14	%	ISO 527
Poisson's ratio	0.35		ISO 527
Flexural modulus, 23°C	1950	MPa	ISO 178
Flexural strength	62	MPa	ISO 178
Charpy notched impact strength, +23°C	3.3	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	M 75		ISO 2039-2
Thermal Properties	Value	Unit	Standard
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow card available	yes		

# DURACON® YF-20

## Polyplastics

Electrical Properties	Value	Unit	Standard
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	2E16	Ohm	IEC 62631-3-2

  

Other Properties	Value	Unit	Standard
Density	1520	kg/m <sup>3</sup>	ISO 1183