

Technical Data Sheet

Durostone[®] EPF S6

GFK-EP

Typical industries

- Generator and Motor
- Electrical Industry
- Electrical Insulating Components
- Mechanical Engineering Industry
- HVDC Transmission

	Test method	Unit	Guideline value
Mechanical properties			
Density	ISO 1183	g / cm ³	2,05
Flexural strength [⊥]	ISO 178	MPa	550
Flexural strength [⊥] +150°C	ISO 178	MPa	275
Modulus of elasticity in flexion [⊥]	ISO 178	MPa	25000
Modulus of elasticity in flexion [⊥] +150°C	ISO 178	MPa	23000
Tensile strength II	ISO 527	MPa	220
Thermal properties			
Temperature index	IEC 60216	T.I.	180
Insulation class	IEC 60085	/	H

