

### Technical Data Sheet

## Durostone<sup>®</sup> EPM 204

GFK-EP

#### Typical characteristics

- Special epoxy (EP) resin matrix reinforced with an e-glass roving mat
- Flame retardant
- Good machinability

#### Typical industries

- Oil and Gas
- Solar Energy
- Renewable Energies
- Electrical Insulating Components
- Electrical Industry

|  | Test method | Unit                               | Guideline value |
|--|-------------|------------------------------------|-----------------|
| <b>Mechanical properties</b>                         |             |                                    |                 |
| Flexural strength <sup>⊥</sup>                       | ISO 178     | MPa                                | 360             |
| Flexural strength <sup>⊥</sup> +150°C                | ISO 178     | MPa                                | 200             |
| Modulus of elasticity in flexion <sup>⊥</sup>        | ISO 178     | MPa                                | 18000           |
| Modulus of elasticity in flexion <sup>⊥</sup> +150°C | ISO 178     | MPa                                | 12000           |
| Compressive strength <sup>⊥</sup>                    | ISO 604     | MPa                                | 450             |
| Compressive strength II                              | ISO 604     | MPa                                | 300             |
| Tensile strength II                                  | ISO 527     | MPa                                | 280             |
| Impact strength II (Charpy)                          | ISO 179     | kJ / m <sup>2</sup>                | 120             |
| Shear strength <sup>⊥</sup>                          | IEC 60893   | MPa                                | 150             |
| Shear strength II                                    | IEC 60893   | MPa                                | 25              |
| <b>Thermal properties</b>                            |             |                                    |                 |
| Temperature index                                    | IEC 60216   | T.I.                               | 180             |
| Coefficient of linear expansion <sup>⊥</sup>         | NF T 51221  | 10 <sup>-6</sup> x K <sup>-1</sup> | 13              |
| Coefficient of linear expansion II                   | NF T 51221  | 10 <sup>-6</sup> x K <sup>-1</sup> | 65              |
| Temperature of deflection under load                 | IEC 893-2   | °C                                 | > 200           |
| Thermal conductivity                                 | ISO 8302    | W/m K                              | 0,36            |
| <b>Flame resistance properties</b>                   |             |                                    |                 |
| Flammability   | NF P92-507  | -                                  | M1              |
| Flammability   | UL94        |                                    | V0              |



|   | Test method | Unit                      | Guideline value  |
|---|-------------|---------------------------|------------------|
| Smoke index                                   | NF P 92501  | -                         | F1               |
| <b>Physical properties</b>                    |             |                           |                  |
| Density                                       | ISO 1183    | g / cm <sup>3</sup>       | 1,9              |
| Water absorption (10mm thickness)             | ISO 62      | %                         | 0,20             |
| <b>Dielectrical properties</b>                |             |                           |                  |
| Electric strength 90°C under oil <sup>⊥</sup> | IEC 60243   | kV / mm                   | 12               |
| Electric strength 90°C under oil II           | IEC 60243   | kV/25mm                   | 60               |
| Relative permittivity (50 Hz)                 | IEC 60250   | $\epsilon_r$              | 5                |
| Dielectric loss factor (50 Hz)                | IEC 60250   | tan $\delta$              | 0,05             |
| Specific surface resistance                   | IEC 60093   | $\Omega$                  | 10 <sup>12</sup> |
| Specific volume resistance                    | IEC 60093   | $\Omega \times \text{cm}$ | 10 <sup>13</sup> |
| Comparative tracking index                    | IEC 60112   | CTI                       | 400              |

