

Technical Data Sheet

Glastherm[®] HT 220

Typical characteristics

- Fibre-reinforced composite material developed for applications in field of thermal insulation (max. continuous operating temperature 220°C)
- Low thermal conductivity

Typical industries

- Chemical Processing Industry
- Mechanical Engineering Industry
- Pipelines
- Oil and Gas

	Test method	Unit	Guideline value
Mechanical properties			
Density	ISO 1183	g / cm ³	1,85
Flexural strength [⊥]	ISO 178	MPa	360
Modulus of elasticity in flexion [⊥]	ISO 178	MPa	18000
Compressive strength ^{1) ⊥}	ISO 604	MPa	500
Compressive strength ^{1) ⊥} +200°C	ISO 604	MPa	360
Tensile strength II	ISO 527	MPa	280
Impact strength [⊥] (Charpy)	ISO 179	kJ / m ²	150
Splitting force II	DIN 53463	N	4000
Thermal properties			
Thermal conductivity ^{2) ⊥}		W / (m * K)	≈ 0,25
Coefficient of linear expansion II	TMA (Mettler)	10 ⁻⁶ x K ⁻¹	≈ 10 - 15
Max. continuous operating temperature		°C	220
Physical properties			
Water absorption (4mm thickness)	ISO 62	%	0,1

