

### Technical Data Sheet

## Glastherm<sup>®</sup> HT LC

#### Typical characteristics

- Fibre-reinforced composite material developed for applications in field of thermal insulation (max. continuous operating temperature 200°C)
- Low thermal conductivity
- Heat resistant

#### Typical industries

- Chemical Processing Industry
- Mechanical Engineering Industry
- Pipelines
- Oil and Gas

	Test method	Unit	Guideline value
<b>Mechanical properties</b>			
Density	ISO 1183	g / cm <sup>3</sup>	1,5
Flexural strength <sup>⊥</sup>	ISO 178	MPa	170
Modulus of elasticity in flexion <sup>⊥</sup>	ISO 178	MPa	10000
Compressive strength <sup>1) ⊥</sup>	ISO 604	MPa	300
Compressive strength <sup>1) ⊥</sup> +200°C	ISO 604	MPa	90
Impact strength <sup>⊥</sup> (Charpy)	ISO 179	kJ / m <sup>2</sup>	80
<b>Thermal properties</b>			
Thermal conductivity <sup>2) ⊥</sup>		W / (m * K)	0,18
Coefficient of linear expansion II	TMA (Mettler)	10 <sup>-6</sup> x K <sup>-1</sup>	≈ 20
Max. continuous operating temperature		°C	200
<b>Physical properties</b>			
Water absorption (4mm thickness)	ISO 62	%	0,2

