

Technical Data Sheet

Lignostone® L II/2-E3-HQ (C1R)

Laminated Densified Wood

Typical characteristics

- High red beech veneer quality; crosswise stacked
- High mechanical strength at low density

Typical industries

- Transformer
- Electrical Industry
- Electrical Insulating Components
- Oil-filled transformers

	Test method	Unit	Guideline value
Mechanical properties			
Density	IEC 61061	g / cm ³	0.85
Flexural strength [⊥]	IEC 61061	MPa	90
Modulus of elasticity in flexion [⊥]	IEC 61061	MPa	8000
Compressive strength [⊥]	ISO 604	MPa	180
Compressive strength II	ISO 604	MPa	60
Shear strength II	IEC 61061	MPa	8
Thermal properties			
Thermal conductivity	DIN 52612	W/m K	0.22
Operating temperature continuous	DIN 7707	°C	105
Temperature limit when drying	DIN 7707	°C	140
Physical properties			
Oil absorption	IEC 61061	%	25
Moisture content	IEC 61061	%	5
Dielectrical properties			
Electric strength 90°C under oil [⊥]	IEC 61061	kV / mm	17
Electric strength 90°C under oil II	IEC 61061	kV/25mm	80
Relative permittivity (50 Hz)	IEC 60250	ε _r	3.7
Dielectric loss factor (50 Hz)	IEC 60250	tan δ	0.01
Specific volume resistance	IEC 60093	Ω x cm	10 ¹²

= perpendicular to the lamination II = parallel to the lamination

