

Technical Data Sheet

Maywoflamm[®] ASA PC

PC / ABS

Typical characteristics

- Vacuum formable
- Flame retardant
- UV-stabilized

Typical industries

- Vacuum Forming

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,23
Water absorption	DIN EN ISO 62	%	0,2
Flammability	UL 94		V0 (1,5mm)
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	57
Elongation at break	DIN EN ISO 527	%	23
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2350
Notched impact strength	DIN EN ISO 179	kJ / m ²	13
Thermal properties			
Melting temperature	ISO 11357-3	°C	> 220
Thermal conductivity	DIN 52612-1	W / (m * K)	0,2
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	68
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	95
Electrical properties			
Surface resistivity	DIN EN 61340	Ω	> 10 ¹²
Volume resistivity	DIN EN 61340	Ω	> 10 ¹²

