

## Technical Data Sheet

# Maywosol ABS ST

ABS / ASA

### Typical characteristics

- Soft-touch effect
- UV-resistant
- Base Material: ABS

### Typical industries

- Vacuum Forming

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,10
Water absorption	DIN EN ISO 62	%	0,3
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	30
Elongation at break	DIN EN ISO 527	%	85,2
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1648
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	16
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	> 180 °C
Thermal conductivity	DIN 52612-1	W / (m * K)	0,17
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	90
Service temperature, long term	Average	°C	85
Service temperature, short term (max.)	Average	°C	100
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	102
<b>Electrical properties</b>			
Surface resistivity	DIN EN 61340	Ω	> 10 <sup>12</sup>
Volume resistivity	DIN EN 61340	Ω	> 10 <sup>12</sup>

