



TEREZ POM 8005 TF 5			
(POM+PTFE)			Ter Plastics
Product Texts			
Medium viscosity standard quality, with 5 % PTFE. For all kind of applications with increased demand of tribological characteristics.			
Rheological properties			
	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties			
	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527-1/-2
Tensile Strength	60	MPa	ISO 527-1/-2
Yield strain	10	%	ISO 527-1/-2
Strain at break	30	%	ISO 527-1/-2
Charpy impact strength (+23°C)	150	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5	kJ/m ²	ISO 179/1eA
Thermal properties			
	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	110	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	150	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Other properties			
	Value	Unit	Test Standard
ISO Data			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1420	kg/m ³	ISO 1183