

Eltex® LGB163N2045

High Density Polyethylene – Milk blow moulding resin



Eltex® LGB163N2045 high density polyethylene is a white homopolymer manufactured by INEOS Polyolefins. It contains 5% titanium dioxide and is intended for the co-extrusion of bottles for the packaging of UHT sterilized milk.

The resin is specifically designed for 3- or 6- layer bottles.

It guarantees the preservation of the organoleptic properties of milk and has the following essential properties :

- High density, ensuring good rigidity of finished products
- A melt viscosity which ensures easy processing
- A very low odour level

It meets EU and FDA regulations governing the approval of materials used in the manufacture of packaging which may come into contact with food products.

INEOS Polyolefins will be happy to supply customers with certificates of conformity to the various national legislations.

Eltex® LGB163N2045

Properties		Test Methods	Values*	Units
Physical				
Density, standard	@ 23°C	ISO 1183 A ⁽¹⁾	1000	kg/m ³
Melt Flow Rate (190°C/2.16 kg)		ISO 1133	0.40	g/10 min
Apparent dynamic viscosity	@ 190°C	INEOS ⁽²⁾	1400	Pa.s
Molecular weight distribution		INEOS	medium	-

(1) Compression-moulded discs, cooled at the rate of 15°C per minute

(2) Apparent dynamic viscosity of the material extruded at 190°C through a 1.0 mm diameter and 15 mm long die, at apparent shear rate 100 s⁻¹

* The table gives the typical values measured on the product. These values should not be considered as specifications.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.