



HY-VIN XH79214

Description	Flexible PVC medical extrusion compound - TOTM Plasticised
Colour	Clear and Tints
Application	Extraction Resistant Tubing
Specification	When extruded under appropriate conditions material expected to comply with requirements of BS2463, Freedom from Toxicity, chemical toxicity requirements of European Pharmacopoeia monograph 3.1.2 and US Pharmacopoeia biological tests for plastics.
Form	Granules
SDS No.	0

<u>PROPERTIES</u>	<u>UNITS</u>	<u>TYPICAL TEST RESULTS</u> (Based on BS2782 Methods)
Density (Varies with colour)	kg/m ³	1190 (Clear42)
Shore 'A' Hardness (15 secs @ 23°C)	Shore 'A'	68
Tensile Strength (@ 500 mm/min)	MPa	17.6
Elongation at Break (@ 500 mm/min)	%	365
Cold flex Temperature	°C	-36

