

## LUSTRAN<sup>®</sup> ABS 266

### ABS

Transparent Grade

#### Description

Lustran ABS 266 resin is a clear injection molding grade of ABS (acrylonitrile butadiene styrene). This transparent, general-purpose grade provides clarity and toughness with ease of processing. The resin is available in transparent tint, color code 000000.

#### Applications

A tough, transparent grade of ABS, Lustran ABS 266 resin is used in housings, toys, lawn and garden applications, and various consumer goods. As with any product, use of Lustran ABS 266 resin in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

#### Drying

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a moisture content ≤ 0.1%. Typical drying conditions are 2 hours at 180°F-190°F (82°C-88°C). Drying for 4 hours at 160°F-170°F (71°C-77°C) is also adequate.

#### Processing

A reciprocating screw injection molding machine is preferred. A general-purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D ratio of 20:1 will ensure melt homogeneity.

For best part quality, use the lower range of the recommended melt temperature with minimum barrel residence time. To avoid excessive residence time in the barrel, volume and weight of the shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine capacity ratio of 0.5-0.75 is recommended.

The melt temperature range of 400-450°F (205-230°C) for Lustran ABS 266 is lower than for other Lustran ABS general-purpose grades because higher melt temperatures may affect transparency and color. Mold temperatures of 110°-150°F (45°-65°C) are recommended for development of maximum strength and clarity, with the hotter end of this range preferred.

Typical processing parameters are noted below. Actual processing conditions will depend on machine size, mold design, material residence time, and shot size.

Typical Injection Molding Conditions	
Barrel Temperatures:	
Rear.....	380° – 430°F (195° – 220°C)
Middle.....	390° – 440°F (200° – 225°C)
Front.....	400° – 450°F (205° – 230°C)
Nozzle.....	400° – 450°F (205° – 230°C)
Melt Temperature.....	400° – 450°F (205° – 230°C)
Mold Temperature.....	110° – 150°F (45° – 65°C)
Injection Pressure.....	10,000 – 16,000 psi
Hold Pressure.....	.50 – 75% of Injection Pressure
Back Pressure.....	.0 – 25 psi
Screw Speed.....	Moderate
Injection Speed.....	High
Cushion .....	1/4 in max
Clamp.....	.2 – 4 ton/in <sup>2</sup>

Additional information on processing may be obtained by contacting an INEOS ABS technical service representative.

Typical Properties* for 1016 Clear Tint Resin	ASTM Test Method (Other)	Units		Lustran® 266 ABS Resin	
		U.S. Conventional	SI Metric	U.S.	SI
<b>General</b>					
Specific Gravity	D 792			1.08	
Density	D 792	lb/in <sup>3</sup>	g/cm <sup>3</sup>	0.039	1.08
Specific Volume	D 792	in <sup>3</sup> /lb	cm <sup>3</sup> /g	25.6	0.93
Mold Shrinkage	D 955	in/in	mm/mm	0.004–0.006	
Melt Flow Rate at 230°C/3.8-kg Load	D 1238	g/10 min		5	
<b>Optical</b>					
Transmittance at 0.100-in Thickness	D 1003	%		86	
Haze at 0.100-in Thickness	D 1003	%		3	
Refractive Index	D 542			1.52	
<b>Mechanical</b>					
Tensile Stress at Yield	D 638	lb/in <sup>2</sup>	MPa	5,400	37
Tensile Stress at Break	D 638	lb/in <sup>2</sup>	MPa	4,200	30
Tensile Elongation at Yield	D 638	%		4	
Tensile Elongation at Break	D 638	%		48	
Tensile Modulus	D 638	lb/in <sup>2</sup>	GPa	286,000	2.0
Flexural Stress at Yield	D 790	lb/in <sup>2</sup>	MPa	8,500	59
Flexural Modulus	D 790	lb/in <sup>2</sup>	GPa	257,000	1.8
Impact Strength, Notched Izod: 0.125-in (3.2-mm) Thickness 73°F (23°C)	D 256	ft·lb/in	J/m	3.3	176
Rockwell Hardness	D 785	R Scale		108	
<b>Thermal</b>					
Deflection Temperature, Unannealed: 0.125-in (3.2-mm) Thickness, 264 psi	D 648	°F	°C	163	73
0.125-in (3.2-mm) Thickness, 66 psi		°F	°C	188	87
0.5-in (12.7-mm) Thickness, 264 psi		°F	°C	180	82
0.5-in (12.7-mm) Thickness, 66 psi		°F	°C	201	94
Coefficient of Linear Thermal Expansion	D 696 (UL746B)	in/in/°F	mm/mm/°C	6.7 E-05	12.1 E-05
Relative Temperature Index: 0.059-in (1.5-mm) Thickness					
Electrical		°F	°C	122	50
Mechanical with Impact		°F	°C	122	50
Mechanical without Impact		°F	°C	122	50
<b>Flammability**</b>					
UL94 Flame Class: 0.059-in (1.5-mm) Thickness	(UL94)	Rating		HB <sup>a</sup>	
0.118-in (3.0-mm) Thickness		Rating		HB <sup>a</sup>	

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

\*\* Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

<sup>a</sup> Clear color.

**INEOS**  
**ABS**

INEOS ABS (USA) Corporation