

LUSTRAN[®] ABS 552

ABS

Extrusion Grade

Description

Lustran ABS 552 resin is a medium-gloss, medium-impact extrusion grade of ABS (acrylonitrile butadiene styrene). It provides a good balance between rigidity and impact strength, and has a stiff melt flow suitable for extrusion and thermoforming. Lustran ABS 552 resin is easy to color with ABS color concentrates. This resin is designed for either profile extrusion or substrate coextrusion and can be used alone or blended with a higher-impact resin. As with any product, use of Lustran ABS 552 resin in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Drying

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a maximum moisture content of 0.03%. Typical drying conditions are 3-4 hours at 180°-200°F (82°-93°C).

Processing for Profile Extrusion

Extruder. To obtain an optimum balance of appearance and mechanical properties, the extruder profile should be set to deliver polymer at a melt temperature between 420° and 480°F (215° and 249°C). A barrel temperature of 420°-465°F (215-240°C) is recommended.

Screw Design. Single- or two-stage screws can be used, although a two-stage screw is preferred. For two-stage screws, a first-stage compression ratio (feed depth to metering depth) of 2.5 – 2.7 and a pump ratio (second-stage metering to first-stage metering) of 1.5 – 2.0 are recommended.

Die. Die temperature settings for Lustran ABS normally range between 410° and 465°F (210° and 241°C). The die should be adjusted to provide uniform polymer melt at the lips. The typical die land length to profile thickness ratio ranges from 15:1 to 20:1.

Please consult an INEOS ABS technical service representative for additional information on profile extrusion.

Processing for Sheet Extrusion

Extruder. To obtain an optimum balance of sheet gloss and mechanical properties, the extruder profile should be set to deliver polymers at a melt temperature between 420° and 480°F (215° and 249°C).

Screw Design. Single- or two-stage screws can be used, although a two-stage screw is preferred. For two-stage screws, a first-stage compression ratio (feed depth to metering depth) of 2.5 – 2.7 and a pump ratio (second-stage metering to first-stage metering) of 1.5 – 2.0 are recommended.

Die. Die temperature settings for Lustran ABS normally range between 410° and 465°F (210° and 241°C). The die should be adjusted to provide uniform polymer melt at the lips.

Roll Stack. Suggested polishing roll settings for Lustran ABS using a standard S wrap are noted below. Specific settings are dependent on roll diameter, sheet gauge and linear speed.

Polishing Roll	Down Stack	Up Stack
Top	180°-220°F (82°-105°C)	180°-220°F (82-105°C)
Middle	145°-185°F (63°-85°C)	170°-210°F (77°-99°C)
Bottom	180°-220°F (82°-105°C)	160°-200°F (71°-93°C)

Additional information on processing may be obtained by contacting an INEOS ABS technical service representative.

Typical Properties* for Natural Resin	ASTM Test Method (Other)	Lustran® ABS 552 Resin**	
		U.S. Conventional	SI Metric
General Specific Gravity Density Specific Volume Melt Flow Rate at 230°C/10-kg Load Melt Flow Index 220°C/10-kg Load Gloss, 60° Sheet (Formed)	D 792 D 792 D 792 D1238 D523	1.05 0.038 lb/in ³ 26.4 in ³ /lb	1.05 1.05 g/cm ³ 0.95 cm ³ /g
Mechanical Tensile Stress at Yield Tensile Modulus Flexural Stress at Yield Flexural Modulus Impact Strength, Notched Izod: 0.125-in (3.2-mm) Thickness 73°F (23°C) 0°F (-18°C) -30°F (-34°C) Instrument Impact: ^a Peak Energy 73°F (23°C) 0°F (-18°C) -30°F (-34°C) Total Energy 73°F (23°C) 0°F (-18°C) -30°F (-34°C) Rockwell Hardness, R Scale	D 638 D 638 D 790 D 790 D 256 D 3763 D 785	5,200 lb/in ² 290,000 lb/in ² 8,600 lb/in ² 290,000 lb/in ² 4.9 ft-lb/in 2.4 ft-lb/in 1.9 ft-lb/in 22 ft-lb 17 ft-lb 12 ft-lb 32 ft-lb 21 ft-lb 13 ft-lb	35.9 MPa 2.0 GPa 59.3 MPa 2.0 GPa 262 J/m 128 J/m 101 J/m 30 J 23 J 16 J 43 J 28 J 18 J
Thermal Deflection Temperature Under Load: Unannealed, 264 psi (1.82 MPa) Unannealed, 66 psi (0.46 MPa) Coefficient of Linear Thermal Expansion Relative Temperature Index: 0.059-in (1.5-mm) Thickness Electrical Mechanical with Impact Mechanical without Impact	D 648 D 696 (UL746B)	190°F 200°F 4.6 E-05 in/in/°F 140°F 140°F 140°F	88°C 97°C 8.3 E-05 mm/mm/°C 60°C 60°C 60°C
Flammability*** UL94 Flame Class: 0.059-in (1.5-mm) Thickness	(UL94)		HB ^b Rating

* These items are provided as general information only. They are approximate values and are not part of the product specifications.

**Properties tested in transverse direction (worst case) on 125-mil extruded sheet specimens with less than 10% orientation unless otherwise noted.

***Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

^a0.5-in dart, 3-in clamp, 7.6 mph

^bNatural color

INEOS
ABS

INEOS ABS (USA) Corporation