

LUSTRAN[®] ABS LK197

ABS

Extrusion Grade

Description

Lustran ABS LK197 resin is a low-gel, high-gloss, medium-impact extrusion grade of ABS (Acrylonitrile Butadiene Styrene). It provides excellent surface appearance, a superior balance between rigidity and impact strength, and excellent melt strength for good thermoformability. It is easy to color with ABS color concentrates.

Applications

Lustran ABS LK197 resin is used in applications that require high gloss and higher rigidity, such as bathtubs, sinks, and shower surrounds for recreational vehicles, and interior liners for ice chests and picnic coolers. As with any product, use of Lustran ABS LK197 resin in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Drying

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a maximum moisture content of 0.03%. Typical drying conditions are 3–4 hours at 180°-200°F (82-93°C).

Processing

Extruder. To obtain an optimum balance of sheet gloss and mechanical properties, the extruder profile should be set to deliver polymers at a melt temperature between 420° and 480°F (215° and 249°C). A barrel temperature of 420°-465°F (215-240°C) is recommended.

Screw Design. Single- or two-stage screws can be used, although a two-stage screw is preferred. For two-stage screws, a first-stage compression ratio (feed depth to metering depth) of 2.5 – 2.7 and a pump ratio (second-stage metering to first-stage metering) of 1.5 – 2.0 are recommended.

Die. Die temperature settings for Lustran ABS normally range between 410° and 465°F (210° and 241°C). The die should be adjusted to provide uniform polymer melt at the lips.

Roll Stack. Suggested polishing roll settings for Lustran ABS using a standard S wrap are noted below. Specific settings are dependent on roll diameter, sheet gauge and linear speed.

Polishing Roll	Down Stack	Up Stack
Top	180°-220°F (82°-105°C)	180°-220°F (82-105°C)
Middle	145°-185°F (63°-85°C)	170°-210°F (77°-99°C)
Bottom	180°-220°F (82°-105°C)	160°-200°F (71°-93°C)

Additional information on processing may be obtained by contacting an INEOS ABS technical service representative.

Typical Physical Properties* for Natural Resin	ASTM Test Method (Other)	Lustran® ABS LK 197 ABS Resin**	
		U.S. Conventional	SI Metric
General			
Specific Gravity	D 792		1.06
Density	D 792	0.038 lb/in ³	1.06 g/cm ³
Specific Volume	D 792	26.1 in ³ /lb	0.94 cm ³ /g
Water Absorption, Immersion at 73°F (23°C): 24 Hours	D 570		0.4 ^m %
Melt Flow Rate at 230°C/10-kg Load	D 1238		9.2 g/10 min
Gloss, 60°, Sheet	D 523		90%
Mechanical			
Tensile Stress at Yield:	D 638		
160°F (71°C)		3,200 lb/in ²	22.1 MPa
73°F (23°C)		5,800 lb/in ²	40.0 MPa
0°F (-18°C)		8,600 lb/in ²	59.3 MPa
Tensile Modulus:	D 638		
160°F (71°C)		220,000 lb/in ²	1.5 GPa
73°F (23°C)		330,000 lb/in ²	2.3 GPa
0°F (-18°C)		370,000 lb/in ²	2.6 GPa
Flexural Stress at Yield:	D 790		
160°F (71°C)		7,200 lb/in ²	49.6 MPa
73°F (23°C)		9,200 lb/in ²	63.4 MPa
-40°F (-40°C)		16,500 lb/in ²	113.8 MPa
Flexural Modulus:	D 790		
160°F (71°C)		280,000 lb/in ²	1.9 GPa
73°F (23°C)		60,000 lb/in ²	2.5 GPa
-40°F (-40°C)		400,000 lb/in ²	2.8 GPa
Impact Strength, Notched Izod:	D 256		
0.125-in (3.2-mm) Thickness			
73°F (23°C)		4.5 ft-lb/in	240 J/m
0°F (-18°C)		2.5 ft-lb/in	133 J/m
-40°F (-40°C)		1.7 ft-lb/in	91 J/m
Instrumented Impact: ^a	D 3763		
Peak Energy			
73°F (23°C)		16 ft-lb	22 J
0°F (-18°C)		14 ft-lb	19 J
-40°F (-40°C)		8 ft-lb	11 J
Total Energy			
73°F (23°C)		22 ft-lb	30 J
0°F (-18°C)		18 ft-lb	24 J
-40°F (-40°C)		10 ft-lb	14 J
Rockwell Hardness	D 785	113 R Scale	
Thermal			
Deflection Temperature Under Load:	D 648		
Unannealed, 264 psi (1.82 MPa)		185°F	85°C
Unannealed, 66 psi (0.46 MPa)		199°F	93°C
Annealed, 264 psi (1.82 MPa)		201°F	94°C
Annealed, 66 psi (0.46 MPa)		214°F	101°C
Coefficient of Linear Thermal Expansion	D 696	5.0 E-05 in/in/°F	9.0 E-05 mm/mm/°C
Relative Temperature Index:	(UL746B)		
1.47-mm (0.058-in) Thickness			
Electrical		140°F	60°C
Mechanical with Impact		140°F	60°C
Mechanical without Impact		140°F	60°C
Flammability***			
UL94 Flame Class:	(UL94)	HB Rating	
1.47-mm (0.058-in) Thickness			
Burn Rate:	D 635		
3.2-mm (0.125-in) Thickness		1.4 ^m in/min	35.6 ^m mm/min

* These items are provided as general information only. They are approximate values and are not part of the product specifications.

** Properties tested in transverse direction (worst case) on 125-mil extruded sheet specimens with less than 10% orientation unless otherwise noted.

*** Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

^a 0.5-in dart, 3-in clamp, 7.6 mph.

^m Tested on injection molded specimen.

INEOS
ABS

INEOS ABS (USA) Corporation