

# Luran S KR2868C

Acrylonitrile Styrene Acrylate / Polycarbonate (ASA/PC)

## TECHNICAL DATASHEET

### DESCRIPTION

The product line Luran® SC, comprising blends of ASA with PC, shows in general high heat and high impact resistance and long-term property retention. Its UV resistance is not only sufficient for all kind of interior applications – incl. unpainted surfaces in light colors – but also for exterior parts with medium weatherability requirements. Luran® S KR2868C provides highest impact properties among all Luran® SC grades.

### FEATURES

- Heat resistance
- Impact strength
- Low temperature toughness
- Colour fastness

### APPLICATIONS

- Truck: exterior body panels
- Housings for electrical & electronic devices

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt Volume Rate, 260 °C/5 kg	ISO 1133	cm <sup>3</sup> /10 min	20
<b>Mechanical Properties</b>			
Charpy Notched Impact Strength, 23 °C	ISO 179/1eA	kJ/m <sup>2</sup>	100
Charpy Notched Impact Strength, -30 °C	ISO 179/1eA	kJ/m <sup>2</sup>	15
Tensile Modulus	ISO 527	MPa	2400
Tensile Stress at Yield, 23 °C	ISO 527	MPa	60
Tensile Strain at Yield, 23 °C	ISO 527	%	4.6
Tensile Stress at Break, 23 °C	ISO 527	MPa	51
Tensile Strain at Break, 23 °C	ISO 527	%	120
Nominal Strain at Break, 23 °C	ISO 527	%	97
Flexural Modulus, 23 °C	ISO 178	MPa	2300
Flexural Strength, 23 °C	ISO 178	MPa	80
Hardness, Ball Indentation	ISO 2039-1	MPa	110
<b>Thermal Properties</b>			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	118

# Luran S KR2868C

Acrylonitrile Styrene Acrylate / Polycarbonate (ASA/PC)

## TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	103
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	123
Coefficient of Linear Thermal Expansion	ISO 11359	10 <sup>-6</sup> /°C	70 - 90
<b>Other Properties</b>			
Density	ISO 1183	kg/m <sup>3</sup>	1150
UL94 rating at 1.5 mm thickness	IEC 60695-11-10	-	HB
Glow wire test (GWFI), 2.0 mm	IEC 60695-2-12	°C	650
Water Absorption, Saturated at 23 °C	ISO 62	%	0.7
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.25
<b>Processing</b>			
Melt Temperature Range	ISO 294	°C	260 - 300
Mold Temperature Range	ISO 294	°C	60 - 90
Drying Temperature	-	°C	100 - 110
Drying Time	-	h	2 - 4
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 0.7