

Product Information

P84[®]NT2 15G HCM

GRAPHITE FILLED (15%) AROMATIC POLYIMIDE

Polyimid P84[®] NT - at a glance

- Excellent performance at high temperatures
- High strength and excellent shape stability
- Very good impact resistance
- High heat deflection temperature
- Very good creep resistance even at elevated temperatures
- Machinable with standard tools
- Low wear and friction behaviour
- Processing by Hot compression molding

Application examples

bushings, seals, bearings components, guides, gear wheels, and valve parts in the automotive and aerospace industries and in industrial equipment.

Key Features

Industrial Sector

Automotive and Mobility, Aircraft and Aerospace, Industry and Engineering

Processing

Hot compression moulding, Machining

Delivery form

Pellets, Granules, Powder

Resistance to

Heat (thermal stability), Fire / burn, Wear / abrasion, Oil / fuels

Electrical

Insulating

Additives

Lubricant

Mechanical properties ISO

| | dry | Unit | Test Standard |
|------------------|---------------|------|---------------|
| Tensile modulus | 595000 | psi | ISO 527 |
| Tensile strength | 15100 | psi | ISO 527 |
| Stress at break | 15100 | psi | ISO 527 |

| | | | |
|---------------------------------------|---------------|----------------------|-------------|
| Strain at break, B | 5.8 | % | ISO 527 |
| Charpy impact strength, +23°C | 21 | ftlb/in ² | ISO 179/1eU |
| Type of failure | C | - | - |
| Charpy notched impact strength, +23°C | 0.714 | ftlb/in ² | ISO 179/1eA |
| Type of failure | C | - | - |
| Compression modulus, 23°C | 657000 | psi | ISO 604 |
| Compressive strength, 23°C | 49200 | psi | ISO 604 |
| Flexural modulus, 23°C | 545000 | psi | ISO 178 |
| Flexural strength, 23°C | 22600 | psi | ISO 178 |

| Thermal properties | dry | Unit | Test Standard |
|----------------------------------------------------|-------------|--------------------------------|----------------------|
| Glass transition temperature, DSC | 691 | °F | ISO 11357-1/-2 |
| Thermal conductivity, LFA, solid state | 3.82 | BTU in/(hr ft ² °F) | ISO 22007-4 |
| Glass transition temperature, DMA, 3 point bending | 747 | °F | ISO 6721-5 |
| Temp. of deflection under load A, 1.80 MPa | 657 | °F | ISO 75-1/-2 |
| Temp. of deflection under load B, 0.45 MPa | 709 | °F | ISO 75-1/-2 |

| Physical properties | dry | Unit | Test Standard |
|----------------------------|-------------|-------------------|----------------------|
| Density | 1.46 | g/cm ³ | ISO 1183 |
| Water absorption, 24h | 0.8 | % | ISO 62, ASTM D 570 |
| Water absorption, 48h | 1.2 | % | ISO 62, ASTM D 570 |
| Shore D hardness | 86 | - | ISO 7619-1 |
| Density | 1.46 | g/cm ³ | ASTM D 792 |

| Polyimid | dry | Unit | Test Standard |
|-----------------|------------|-------------|----------------------|
|-----------------|------------|-------------|----------------------|

Tensile test

| | | | |
|------------------------|---------------|-----|---------|
| Tensile modulus, 23°C | 595000 | psi | ISO 527 |
| Tensile strength, 23°C | 15100 | psi | ISO 527 |

| | | | |
|-----------------------|------------|---|---------|
| Strain at break, 23°C | 5.8 | % | ISO 527 |
|-----------------------|------------|---|---------|

Flexural test

| | | | |
|-------------------------|---------------|-----|---------|
| Flexural modulus, 23°C | 545000 | psi | ISO 178 |
| Flexural strength, 23°C | 22600 | psi | ISO 178 |

Characteristics

Applications

Electrical and Electronical, General purpose

Color

Natural color, Black

Processing

Compression molding

Additives

Conductive agent, Inorganic fillers

Special Characteristics

PTFE-free, Amorphous, High heat resistant, Non-dripping, Self-extinguishing, Thermally conductive

Chemical Resistance

Acid resistance, Solvent resistance, Grease resistance, Oil resistance, Radiation resistance, Fuel resistance

Features

Creep resistance, Low coefficient of friction, Lightweight

Compression molding

Hot compression molding

Production of big semi-finished parts (plates, rods, tubes)

Molding at high pressure of 400 kg/cm² and temperature between 350 and 380 °C.

Cycle time = hours

Processing of precise parts by machining

Best mechanical properties