

Product Information

P84®UHT 05P DF

HIGH TEMPERATURE RESISTANCE, UNFILLED POLYIMIDE

Polyimid P84®UHT - at a glance

- Excellent thermal-oxidative stability (use up to 300 ° C)
- High mechanical strength and dimensional stability even at very high temperatures
- Good creep resistance under load even at high temperatures
- Easy machinability with standard tools for metals
- Excellent tribological properties, high wear resistance
- Processing by direct forming

Application examples

bushings, seals, bearings components, guides, gear wheels, and valve parts in the automotive and aerospace industries and in industrial equipment.

Key Features

Industrial Sector

Automotive and Mobility, Aircraft and Aerospace, Industry and Engineering

Processing

Press and sintering, Machining

Delivery form

Powder

Resistance to

Heat (thermal stability), Fire / burn, Wear / abrasion, Oil / fuels

Electrical

Insulating

Additives

Release agent, Unfilled

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	740000	psi	ISO 527
Tensile strength	16500	psi	ISO 527
Stress at break	16500	psi	ISO 527
Strain at break, B	4.2	%	ISO 527

Charpy impact strength, +23°C	16.6	ftlb/in ²	ISO 179/1eU
Type of failure	C	-	-
Charpy notched impact strength, +23°C	1.43	ftlb/in ²	ISO 179/1eA
Type of failure	C	-	-
Compression modulus, 23°C	666000	psi	ISO 604
Compressive strength, 23°C	57300	psi	ISO 604
Flexural modulus, 23°C	606000	psi	ISO 178
Flexural strength, 23°C	23100	psi	ISO 178
Flexural strain at break, 23°C	4.5	%	ISO 178

Thermal properties	dry	Unit	Test Standard
Glass transition temperature, DSC	554	°F	ISO 11357-1/-2
Thermal conductivity, LFA, solid state	2.29	BTU in/(hr ft ² °F)	ISO 22007-4
Temp. of deflection under load A, 1.80 MPa	513	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	550	°F	ISO 75-1/-2
RTI 50% flexural strength	565	°F	IEC 60216
HIC	11	K	IEC 60216

Physical properties	dry	Unit	Test Standard
Density	1.36	g/cm ³	ISO 1183
Water absorption, 24h	0.8	%	ISO 62, ASTM D 570
Water absorption, 48h	1	%	ISO 62, ASTM D 570
Shore D hardness	87	-	ISO 7619-1
Density	1.36	g/cm ³	ASTM D 792

Powder properties	dry	Unit	Test Standard
Bulk density, powder	400	g/l	EN ISO 60

Polyimid

dry

Unit

Test Standard

Thermal Properties Polyimid

RTI 50% flexural strength	565	°F	IEC 60216
HIC	11	K	IEC 60216

Tensile test

Tensile modulus, 23°C	740000	psi	ISO 527
Tensile strength, 23°C	16500	psi	ISO 527
Strain at break, 23°C	4.2	%	ISO 527

Flexural test

Flexural modulus, 23°C	606000	psi	ISO 178
Flexural strength, 23°C	23100	psi	ISO 178
Flexural strain at break, 23°C	4.5	%	ISO 178

Characteristics

Applications

Displays, Electrical and Electronical, General purpose, IT and telecommunication

Processing

DF Direct forming

Special Characteristics

Amorphous, High heat resistant, Non-dripping, Self-extinguishing

Features

Creep resistance, Low coefficient of friction, Lightweight

Color

Natural color, Beige

Additives

Release agent

Chemical Resistance

Acid resistance, Solvent resistance, Grease resistance, Oil resistance, Oxidation resistance, Radiation resistance, Fuel resistance

Compression molding

Direct forming

High number of small parts

Production of green parts at ambient temperature and very high pressure between 2 and 4 t/cm²

Cycle time = seconds

Subsequent sintering at temperatures between 395 and 425°C

No or little machining necessary