

Styrolux 656C

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

DESCRIPTION

The product line Styrolux® comprises clear styrene butadiene copolymers. The grades have in general an intrinsic toughness, are easy to process and work as modifiers and compatibilizers not only in polystyrene but in many other polymers, e.g. polyolefins. For all Styrolux® grades food contact statements are available upon request. Styrolux® 656C shows enhanced flow properties and is used almost exclusively used for injection molding of rigid, tough parts, requiring highest levels of clarity and surface gloss. 656C is also offered for medical applications and is Gamma, X-ray & ETO sterilizable.

FEATURES

- Easy processing
- Sterilisable(ETO,NO2,Irradiation)
- Transparency

APPLICATIONS

- Food contact application
- Medical devices
- Rigid packaging
- Cosmetic packaging
- Toys, sports & leisure

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	16
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	1
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	20
Tensile Modulus	ISO 527	MPa	1600
Tensile Stress at Yield, 23 °C	ISO 527	MPa	35
Tensile Strain at Yield, 23 °C	ISO 527	%	2.5
Tensile Strain at Break, 23 °C	ISO 527	%	20
Nominal Strain at Break, 23 °C	ISO 527	%	20
Tensile Creep Modulus (1h)	ISO 899	MPa	1550
Flexural Strength, 23 °C	ISO 178	MPa	40
Hardness, Shore D	ISO 868	-	70
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	60

Styrolux 656C

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	59
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	73
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	60 - 90
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.579
Haze	ASTM D 1003	%	< 1.5
Light Transmission at 550 nm	ASTM D 1003	%	90
Other Properties			
Density	ISO 1183	kg/m ³	1020
Water Absorption, Saturated at 23 °C	ISO 62	%	0.07
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1
Melt Temperature Range	ISO 294	°C	180 - 250
Mold Temperature Range	ISO 294	°C	30 - 50