

Styrolux T

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

DESCRIPTION

The product line Styrolux® comprises clear styrene butadiene copolymers. The grades have in general an intrinsic toughness, are easy to process and work as modifiers and compatibilizers not only in polystyrene but in many other polymers, e.g. polyolefins. For all Styrolux® grades food contact statements are available upon request. Styrolux® T is a very tough grade designed to be blended with Styrolux® S in shrink film applications and enables high performance in film extrusion.

FEATURES

- Controlled shrinkability
- Well extrudable
- Toughness
- Transparency

APPLICATIONS

- Food contact applications
- Shrink sleeves

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	12
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	2
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	> 80
Tensile Modulus	ISO 527	MPa	1200
Tensile Stress at Yield, 23 °C	ISO 527	MPa	25
Tensile Strain at Yield, 23 °C	ISO 527	%	3
Tensile Stress at Break, 23 °C	ISO 527	MPa	22
Tensile Strain at Break, 23 °C	ISO 527	%	250
Nominal Strain at Break, 23 °C	ISO 527	%	250
Flexural Modulus, 23 °C	ISO 178	MPa	1000
Flexural Strength, 23 °C	ISO 178	MPa	32
Hardness, Shore D	ISO 868	-	58
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	46

Styrolux T

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	50
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.57
Haze	ASTM D 1003	%	< 2
Light Transmission at 550 nm	ASTM D 1003	%	89
Other Properties			
Density	ISO 1183	kg/m ³	1020
Water Absorption, Saturated at 23 °C	ISO 62	%	0.07
Processing			
Melt Temperature Range	ISO 294	°C	180 - 250
Mold Temperature Range	ISO 294	°C	30 - 50
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1