

Product Information

TROGAMID® CX9710 NC

MEDIUM-VISCOSITY AND TRANSPARENT POLYAMIDE FOR INJECTION MOLDING WITH RELEASE AGENT



TROGAMID® CX9710 is a medium-viscosity and transparent polyamide for injection molding for the manufacture of parts in the optical industry.

The material absorbs only small amounts of water. Components made from this material therefore show excellent dimensional stability under changing ambient humidity as well as consistent UV-stability and chemical resistance.

TROGAMID® CX9710 is supplied as spherical pellets in moisture-proof packaging.

Pigmentation may affect values.

Key Features

Industrial Sector

Automotive and Mobility, Aircraft and Aerospace, Industry and Engineering, Optics, Sports and Lifestyle

Resistance to

Heat (thermal stability), Hydrolysis / hot water, UV / light / weathering

Processing

Injection molding, Extrusion

Conformity

Food contact

Optics

Transparent, High gloss

Additives

Release agent, Unfilled

Mechanical properties ISO

	dry / cond	Unit	Test Standard
Tensile modulus	203000 / -	psi	ISO 527
Tensile strength	8700 / -	psi	ISO 527
Yield stress	8700 / -	psi	ISO 527
Yield strain	8 / -	%	ISO 527

Stress at 50% strain	6090 / -	psi	ISO 527
Stress at break	9860 / -	psi	ISO 527
Nominal strain at break, tB	190 / -	%	ISO 527
Tensile creep modulus, 0,5% Strain, 1h	* / 203000	psi	ISO 899-1
Tensile creep modulus, 0,5% Strain, 1000h	* / 102000	psi	ISO 899-1
Charpy impact strength, +23°C	N / -	ftlb/in ²	ISO 179/1eU
Charpy impact strength, 0°C	N / -	ftlb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	N / -	ftlb/in ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5.23 / 4.99	ftlb/in ²	ISO 179/1eA
Type of failure	C / C	-	-
Charpy notched impact strength, 0°C	6.66 / -	ftlb/in ²	ISO 179/1eA
Type of failure	C / -	-	-
Charpy notched impact strength, -30°C	6.18 / -	ftlb/in ²	ISO 179/1eA
Type of failure	C / -	-	-
Flexural modulus, 23°C	247000 / -	psi	ISO 178
Flexural stress at conv. deflection, 23°C	7250 / -	psi	ISO 178
Flexural strength, 23°C	13100 / -	psi	ISO 178
Flexural strain at flexural strength, 23°C	9 / -	%	ISO 178
Flexural strain at break, 23°C	N / -	%	ISO 178

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature	482 / *	°F	ISO 11357-1/-3
Glass transition temperature, DSC	284 / *	°F	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	226 / *	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	252 / *	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	275 / *	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	266 / *	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	5.0E-5 / *	in/in/°F	ISO 11359-1/-2

Coeff. of linear therm. expansion, 23°C to 55 °C, normal	5.0E-5 / *	in/in/°F	ISO 11359-1/-2
Melting Temperature	482	°F	ASTM D 3418

Physical properties	dry / cond	Unit	Test Standard
Density	1.02 / -	g/cm ³	ISO 1183
Water absorption	3.5 / *	%	Sim. to ISO 62
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Shore D hardness	81^[b] / -	-	ISO 7619-1
Ball indentation hardness	16000 / -	psi	ISO 2039-1
Density	1.02	g/cm ³	ASTM D 792

b: 3 seconds

Burning Behav.	dry / cond	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0630 / *	in	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.0315 / *	in	-
Glow Wire Flammability Index (GWFI)	1470	°F	IEC 60695-2-12
GWFI - thickness tested	0.0394	in	-
Glow Wire Ignition Temperature (GWIT)	1430	°F	IEC 60695-2-13
GWIT - thickness tested	0.0394	in	-

Electrical properties	dry / cond	Unit	Test Standard
Surface resistivity, E	* / 1E13	Ohm	IEC 62631-3-2
Relative permittivity, 100Hz	3.6 / -	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.2 / -	-	IEC 62631-2-1
Dissipation factor, 100Hz	120 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	325 / -	E-4	IEC 62631-2-1
Dielectric strength, AC, S20/P50	686 / -	V/mil	Sim. to IEC 60243-1

CTI, test solution A, 50 drops value	600 / -	-	IEC 60112
Assessment of the insulation group	I	-	DIN EN 60664-1

Rheological properties	dry / cond	Unit	Test Standard
Melt volume-flow rate, MVR	20 / *	cm ³ /10min	ISO 1133
Temperature	285 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	0.7 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

Polymer analytics	dry / cond	Unit	Test Standard
Viscosity number	4150 / *	in ³ /lb	ISO 307, 1157, 1628

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	536	°F	ISO 294
Injection Molding, mold temperature	176	°F	ISO 294
Injection Molding, injection velocity	7.87	in/s	ISO 294
Injection Molding, pressure at hold	10200	psi	ISO 294

Characteristics

Applications

Electrical and Electronical, Hygiene and cosmetics, Packaging

Processing

Film extrusion, Profile extrusion, Sheet extrusion, Blow molding, Thermoforming

Special Characteristics

Environmental stress crack resistance, Light-stabilized, U.V. stabilized, Medium viscosity

Color

Natural color

Additives

Release agent

Delivery form

Spherical pellets

Chemical Resistance

General chemical resistance

Chemical Media Resistance

Acids

- ✘ Sulfuric Acid (38% by mass) (23°C)

Alcohols

- ✔ Isopropyl alcohol (23°C)
- ✔ Methanol (23°C)
- ✔ Ethanol (23°C)

Hydrocarbons

- ✔ Toluene (23°C)

Ketones

- ✔ Acetone (23°C)

Mineral oils

- ✔ SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✔ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Other

- ✔ Ethyl Acetate (23°C)

Rheological calculation properties	dry	Unit	Test Standard
Min. mold temperature	140	°F	-
Max. mold temperature	212	°F	-
Min. melt temperature	536	°F	-
Max. melt temperature	572	°F	-