

Product Information

**VESTAKEEP® 2000 CF30**

**CARBON FIBER-REINFORCED, MEDIUM VISCOSITY POLYETHER ETHER KETONE**



**VESTAKEEP® 2000 CF30** is a medium-viscosity, carbon fiber-reinforced (30%) polyether ether ketone for injection molding.

The semi-crystalline polymer features superior, mechanical, thermal and chemical resistance. Parts made from VESTAKEEP® 2000 CF30 are of low flammability.

VESTAKEEP® 2000 CF30 can be processed by common injection machines for thermoplastics.

We recommend a melt temperature between 380°C and 400°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 2000 CF30 is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may effect values.

For information about processing of VESTAKEEP® 2000 CF30, please follow the general recommendations in our brochure "VESTAKEEP® PEEK-Processing Guidelines".

**Key Features**

**Industrial Sector**

Aircraft and Aerospace, Industry and Engineering

**Resistance to**

Fire / burn

**Processing**

Injection molding

**Additives**

Carbon fibers

**Delivery form**

Pellets, Granules

**Mechanical properties ISO**

Tensile modulus

dry

**3.48E6**

Unit

psi

Test Standard

ISO 527

Tensile strength	<b>36400</b>	psi	ISO 527
Stress at break	<b>36400</b>	psi	ISO 527
Strain at break, B	<b>1.85</b>	%	ISO 527
Poisson's ratio, 23°C	<b>0.44</b>	-	ISO 527
Anisotropy ratio, tensile modulus	<b>0.52</b>	-	-
Anisotropy ratio, tensile strength	<b>0.63</b>	-	-
Charpy impact strength, +23°C	<b>24.3</b>	ftlb/in <sup>2</sup>	ISO 179/1eU
Type of failure	<b>C</b>	-	-
Charpy impact strength, -30°C	<b>21.4</b>	ftlb/in <sup>2</sup>	ISO 179/1eU
Type of failure	<b>C</b>	-	-
Charpy notched impact strength, +23°C	<b>3.81</b>	ftlb/in <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-
Charpy notched impact strength, -30°C	<b>3.81</b>	ftlb/in <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-
Flexural modulus, 23°C	<b>3.12E6</b>	psi	ISO 178
Flexural stress at break, 23°C	<b>56600</b>	psi	ISO 178
Flexural strain at break, 23°C	<b>2.1</b>	%	ISO 178

<b>Mechanical properties ASTM</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
tensile modulus, annealed	<b>3.3E6</b>	psi	ASTM D 638
Stress at break, 23°C, annealed	<b>2</b>	%	ASTM D 638
Strain at break, 23°C, annealed	<b>36000</b>	psi	ASTM D 638

<b>Thermal properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Melting temperature	<b>644</b>	°F	ISO 11357-1/-3
Glass transition temperature, DSC	<b>295</b>	°F	ISO 11357-1/-2
Temp. of deflection under load A, 1.80 MPa	<b>626</b>	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	<b>644</b>	°F	ISO 75-1/-2

Vicat softening temperature A, 10 N, 50 K/h	<b>649</b>	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	<b>644</b>	°F	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	<b>5.56E-6</b>	in/in/°F	ISO 11359-1/-2
Melting Temperature	<b>644</b>	°F	ASTM D 3418

Physical properties	dry	Unit	Test Standard
Density	<b>1.41</b>	g/cm <sup>3</sup>	ISO 1183
Water absorption	<b>0.4</b>	%	Sim. to ISO 62
Density	<b>1.41</b>	g/cm <sup>3</sup>	ASTM D 792

Burning Behav.	dry	Unit	Test Standard
UL Yellow Card available	<a href="#">yes</a>	-	-
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>0.0630</b>	in	-
Oxygen index	<b>47</b>	%	ISO 4589-1/-2
Limiting Oxygen Index	<b>47</b>	%	ASTM D 2863
Glow Wire Flammability Index (GWFI)	<b>1760</b>	°F	IEC 60695-2-12
GWFI - thickness tested	<b>0.0787</b>	in	-
Glow Wire Ignition Temperature (GWIT)	<b>1610</b>	°F	IEC 60695-2-13
GWIT - thickness tested	<b>0.0787</b>	in	-

Electrical properties	dry	Unit	Test Standard
Volume resistivity, V	<b>10000</b>	Ohm*m	IEC 62631-3-1
Relative permittivity, 1MHz	<b>17</b>	-	IEC 62631-2-1
Dissipation factor, 1MHz	<b>2300</b>	E-4	IEC 62631-2-1


Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	<b>19</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>400</b>	°C	-

Load	<b>5</b>	kg	-
Molding shrinkage, parallel	<b>0</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>0.4</b>	%	ISO 294-4, 2577
Mold temperature	<b>356</b>	°F	-
Melt temperature	<b>734</b>	°F	-

<b>Test specimen production</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Injection Molding, melt temperature	<b>716</b>	°F	ISO 294
Injection Molding, mold temperature	<b>356</b>	°F	ISO 294
Injection Molding, injection velocity	<b>7.87</b>	in/s	ISO 294
Injection Molding, pressure at hold	<b>17400</b>	psi	ISO 294

**Diagrams**

**Stress-strain (anisotropy)**



**Characteristics**

**Applications**

Electrical and Electronical

**Special Characteristics**

High heat resistant

**Color**

Natural color

**Delivery form**

Cylindrical pellets

**Chemical Resistance**

Aging resistance, General chemical resistance

**Chemical Media Resistance**

**Acids**

- ✓ Acetic Acid (5% by mass) (23°C)
- ✓ Citric Acid solution (10% by mass) (23°C)
- ✓ Hydrochloric Acid (36% by mass) (23°C)
- ✗ Nitric Acid (40% by mass) (23°C)
- ✓ Sulfuric Acid (5% by mass) (23°C)
- ✓ Chromic Acid solution (40% by mass) (23°C)

#### Bases

- ✓ Sodium Hydroxide solution (35% by mass) (23°C)
- ✓ Sodium Hydroxide solution (1% by mass) (23°C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23°C)

#### Alcohols

- ✓ Isopropyl alcohol (23°C)
- ✓ Methanol (23°C)
- ✓ Ethanol (23°C)

#### Hydrocarbons

- ✓ n-Hexane (23°C)
- ✓ Toluene (23°C)
- ✓ iso-Octane (23°C)

#### Ketones

- ✓ Acetone (23°C)

#### Ethers

- ✓ Diethyl ether (23°C)

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23°C)
- ✓ Insulating Oil (23°C)

#### Standard Fuels

- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

#### Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

#### Other

- ✓ Ethyl Acetate (23°C)

- ✓ Hydrogen peroxide (23°C)
- ✓ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ Water (23°C)
- ✓ Deionized water (90°C)

**Rheological calculation properties**

	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Min. mold temperature	<b>320</b>	°F	-
Max. mold temperature	<b>392</b>	°F	-
Min. melt temperature	<b>716</b>	°F	-
Max. melt temperature	<b>752</b>	°F	-