

Product Information

VESTAKEEP® 2000 UFP10

UNREINFORCED, MEDIUM-VISCOSITY POLYETHER ETHER KETONE ULTRA-FINE POWDER



VESTAKEEP® 2000 UFP10 is an unreinforced, medium-viscosity polyether ether ketone ultra-fine powder. The product can be used for coatings according to the tribo-method or can be applied in a suspension.

The semi-crystalline polymer features superior thermal and chemical resistance. VESTAKEEP® 2000 UFP10 is of low flammability.

VESTAKEEP® 2000 UFP10 is supplied as a powder in boxes with moisture-proof polyethylene liners.

Pigmentation may affect values.

Values measured on VESTAKEEP® 2000 P.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Key Features

Industrial Sector

Automotive and Mobility, Aircraft and Aerospace, Energy, Oil and Gas

Processing

Press and sintering, Coating

Delivery form

Powder

Optics

Laser transparent

Resistance to

Heat (thermal stability), Fire / burn, Hydrolysis / hot water, UV / light / weathering, Wear / abrasion, Fatigue resistance, Oil / fuels

Electrical

Insulating

Conformity

Food contact

Additives

Unfilled

Mechanical properties ISO

Tensile modulus

dry

537000

Unit

psi

Test Standard

ISO 527

Tensile strength	14500	psi	ISO 527
Yield stress	14500	psi	ISO 527
Yield strain	5	%	ISO 527
Stress at break	10200	psi	ISO 527
Nominal strain at break, tB	30	%	ISO 527
Charpy impact strength, +23°C	N	ftlb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	N	ftlb/in ²	ISO 179/1eU
Charpy notched impact strength, +23°C	2.85	ftlb/in ²	ISO 179/1eA
Type of failure	C	-	-
Charpy notched impact strength, -30°C	2.85	ftlb/in ²	ISO 179/1eA
Type of failure	C	-	-

Thermal properties	dry	Unit	Test Standard
Melting temperature	644	°F	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	311	°F	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	401	°F	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	635	°F	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	590	°F	ISO 306
Melting Temperature	644	°F	ASTM D 3418

Physical properties	dry	Unit	Test Standard
Density	1.3	g/cm ³	ISO 1183
Density	1.3	g/cm ³	ASTM D 792

Burning Behav.	dry	Unit	Test Standard
Burnin behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.1260	in	-

Rheological properties

	dry	Unit	Test Standard
Melt volume-flow rate, MVR	72	cm ³ /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-

Powder properties

	dry	Unit	Test Standard
Bulk density, powder	230	g/l	EN ISO 60
Particle size, Max.	55	µm	ISO 13320, DIN ISO 8130-13
Particle size, D(50)	11	µm	ISO 13320, DIN ISO 8130-13

Characteristics

Applications

Electrical and Electronical

Processing

Electrostatic coating

Special Characteristics

Semi-crystalline, Medium viscosity

Features

Dispersion coating

Color

Natural color

Delivery form

Ultrafine powder (UFP)

Chemical Resistance

General chemical resistance